

Flame Retardant Corrosive Resistant Conductive Fabric Article and Method

Technical Field

The present invention relates to flame resistant conductive fabrics and
5 more particularly to such a fabric having utility as a component of
electromagnetic interference (EMI) and radio frequency interference (RFI)
shielding products.

Background of the Invention

Many modern electronic devices require flame retardant approval from
10 Underwriters Laboratories (UL). These include such devices as personal and
business computers, various radio frequency and microwave devices,
equipment used in telephone base stations and switching electronics. If each
individual component of such apparatus has UL approval, the overall
apparatus does not require flame-retardant approval. Thus, ensuring that each
15 component has UL approval avoids the need for UL testing of the entire
apparatus and reduces cost to the apparatus manufacturer.

The need for flame retardant approval of individual components
extends to fabric materials that may be used in various shielding components
of the apparatus. Shielding components protect the electrical or electronic
20 components of the apparatus from electromagnetic interference (EMI).
Electromagnetic interference is understood to mean undesired conducted or
radiated electrical disturbances from an electric or electronic apparatus,
including transients, which can interfere with the operation of other electrical
or electronic apparatus. Such disturbances can occur anywhere in the
25 electromagnetic spectrum. Radio frequency interference (RFI) refers to
disturbances in the radio frequency portion of the electromagnetic spectrum
but often is used interchangeably with electromagnetic interference. Both
electromagnetic and radio frequency interference are referred to hereafter as
EMI.

11/11/11 11:11:11

Electronic devices not only are sources of EMI, but also the operation of such devices may be adversely affected by the emission of EMI from other sources. Consequently, electric or electronic apparatus susceptible to electromagnetic interference generally must be shielded in order to operate properly.

Many shielding applications such as gaskets, cable shields, grounding straps, conductive tapes, laminate shields among others, utilize a conductive fabric in its construction. For example, a gasket for use between a computer cabinet and a cabinet door may comprise a resilient core enclosed in a conductive fabric. Conductive fabrics generally are formed of polymeric fibers and are either woven or non-woven. To render the fabric conductive, the fibers may include particles of a conductive material or the fabric may be coated with a conductive metal by various methods including electroless plating and vapor deposition among others.

One method of providing a conductive fabric with flame retardant properties is to incorporate a flame retardant into the material of the fabric. For example, U. S. Patent No. 5,674,606 discloses dispersing alumina trihydrate in a polymeric material used to form a conductive fabric. A further alternative is to form the fabric of fiberglass. While a fiberglass fabric is inherently fire resistant, it is brittle and subject to cracking in dynamic applications. Substrate fabrics of polymeric materials generally are more flexible and durable than fiberglass and are preferred. The problem is that prior attempts to produce a conductive polymeric fabric having flame-retardant properties suitable for use as an EMI shield have not been entirely satisfactory.

The industry standard for a flame retardant EMI shielding fabric is a fabric having an Underwriters Laboratories rating for very thin material (VTM) of zero burn in a vertical burn test (described hereinbelow). A VTM burn rating of zero is particularly difficult to achieve for metalized polymeric fabrics because the metal coating acts as an accelerant to combustion.

Incorporating a flame retarding material into the formulation of the polymeric material of the fabric provides a degree of protection but does not completely solve the problem. Applying a flame-retardant material over the conductive metalized surface may provide a UL approved material. However,
 5 the amount of flame retardant that must be applied over the metalized surface in order to obtain the UL VTM zero burn rating (vertical burn test) forms such a thick layer that it significantly decreases the surface conductivity of the metalized fabric. Since high surface conductivity is a desirable attribute of EMI shielding material, a material having a low surface conductivity renders it
 10 unacceptable for such use. Low surface conductivity also is caused by corrosion of the conductive metal layer and conventional flame-retardant materials accelerate galvanic corrosion of the conductive metal. This is another reason why applying a flame-retardant coating to the metalized surface of a conductive fabric has not been an acceptable solution.

15 Accordingly, it is an object of the present invention to provide a electrically conductive polymeric fabric having flame retardant properties.

Another object of the present invention is to provide a conductive polymeric fabric that has an Underwriters Laboratories vertical burn test VTM flammability rating of zero.

20 A further object of the present invention is to provide a flame retardant conductive polymeric fabric that is corrosion resistant so as to maintain a high degree of surface conductivity over time.

Yet another object of the present invention is to provide method of making a flame retardant conductive polymeric fabric suitable for use in EMI
 25 applications.

Summary of the Invention

In accordance with the present invention, it has been unexpectedly found that applying a fire retardant material directly to the surface of a
 30 polymeric fabric and then applying a conductive metal coating over the fire

retardant, provides a fire retardant fabric without compromising high surface conductivity. The application of the fire retardant directly to the fabric surface unexpectedly provides the fabric with a greater flame-retardant property than applying the fire retardant over the surface of the metal coating. Following the teachings of the present invention, a conductive polymeric fabric having

5 flame-retardant properties is obtained using less of the flame-retardant material and without compromising the surface conductivity.

The flame-retardant electrically conductive article of the present invention includes a substrate of a woven or non-woven fabric of a polymeric material such as a polyamide, polyester or acrylic. A flame-retardant coating first is applied directly to the surface of the fabric. Flame retardant materials are well known. These include for example melamine and neoprene. Other flame-retardant materials include a halogenated or non-halogenated flame-retardant material uniformly dispersed in a suitable carrier. For purposes of the present invention the carrier preferably is a liquid that after application to the surface of the fabric, dries, cures or polymerizes *in situ* to form a thin polymeric film bonded to the fabric. This allows the flame retardant to be uniformly distributed in a thin polymeric film matrix applied to the surface of the fabric by dipping, wiping or spraying.

After a thin film of the flame-retardant coating is applied, a conductive metal is laid down over the surface of the flame-retardant coating. Any suitable plating process including electroplating or electroless plating may be used to apply the metal coating. In a preferred process, the conductive metal coating is applied by vapor deposition. In one method, the conductive coating is applied in three successive layers. A first applied layer is a metal, an alloy or a nonmetal that adheres to the flame-retardant polymeric film. A second applied layer is a highly conductive metal such as silver and a third layer is a corrosion and abrasion resistant layer also of a metal, an alloy or a nonmetal. Etching the surface of the flame-retardant coating with a plasma or corona

discharge may improve the adherence of the metal to the flame-retardant coating,

It is believed that improved flame-retardant properties of the article result from separating the flammable polymeric fabric substrate from the conductive metal by disposing a layer of the flame-retardant between the two. By separating the metal from the flammable polymeric fabric, the fabric is insulated from the heat generated and retained by the metal when exposed to a flame. When exposed to flame or heat, the separation as described above prevents the heated metal from igniting or supporting the combustion of the fabric substrate.

This is in contrast with prior art constructions wherein the metal is disposed directly on the fabric substrate and a flame-retardant is then coated onto the metal. In this prior art construction it is believed that even though the fabric may itself contain a flame-retardant and a flame-retardant is coated over the metalized surface, the heating of the metal in direct contact with the fabric causes or promotes the combustion of the fabric.

Accordingly, the present invention may be characterized in one aspect thereof by a flame retardant metalized fabric article comprising:

- 20
- a) a polymeric fabric substrate having a reverse side and an obverse side;
 - b) a conductive metal layer on one side of the substrate; and
 - c) a flame-retardant coating intermediate the conductive metal layer and the polymeric fabric substrate.

In another aspect, the present invention may be characterized by a
25 method of forming a flame-retardant conductive polymeric fabric by the steps
of:

- a) applying a flame-retardant coating directly onto the surface of a polymeric fabric; and
- b) applying a conductive metal onto the surface of the flame-retardant coating.

Description of the Drawings

Figure 1 is a cross sectional view showing a portion of the flame-retardant conductive fabric article of the present invention; and

- 5 Figures 2-4 are views similar to Figure 1 only showing other embodiments of the invention

Detailed Description of the Invention

- Referring to the drawings, Figure 1 shows a flame-retardant conductive
10 fabric article of the present invention generally indicated at 10. The article includes a substrate 12 of a polymeric material such as nylon, polyester or acrylic formed as a woven or non-woven fabric. Other flammable or non-flammable fabrics may also be used.

- Coated onto an obverse side 13 of the fabric is a flame-retardant layer
15 14. A flame-retardant coating generally comprises a material that can be applied as a liquid to the surface of the fabric and forms a thin film when it is dried, cured or polymerized. Suitable flame-retardant materials include melamine and neoprene which are themselves flame-retardant. Other materials include a film-forming carrier such as polyurethane or an acrylic that
20 incorporates any halogenated or non-halogenated flame-retardant additive including alumina trihydrate among others.

- Application of the flame-retardant coating is by dipping, spraying or wiping so as to apply the carrier as a thin film over the surface of the fabric. While not shown, it should be appreciated that at least some portion of the
25 liquid carrier may penetrate into the body of the fabric. After application, the flame-retardant is allowed to dry, cure or polymerize to form a thin polymeric film layer 14 that bonds with the polymeric fabric of the substrate. One or more applications of the flame-retardant material can be made to provide a desired film thickness.

layers of the metalized layer 16 may be deposited in sequence by vapor deposition.

Abrasion resistance, corrosion resistance and galvanic compatibility also are provided by a thin outer coating of an organic material such as an acrylic, polyurethane, polyester or polycarbonate among others. Even though these materials are non-conductive, a thin layer will provide the desired protection without materially decreasing the conductivity of the metal layer beneath.

It further is possible to improve the shielding effectiveness of the film by adding any of the organic materials noted above, among others, as a thin dielectric layer between metal layers to provide capacitance coupling. This is shown in the embodiment of Figure 3 wherein the conductive metal layer 20 includes a dielectric layer 24 disposed between adjacent silver layers 20a and 20b. The fabric itself also can function as a dielectric. In this case, as shown in Figure 4, the opposite sides of the fabric 12 are first both coated with a flame-retardant coating 30 and then coated with conductive metal layers 32,34.

The structure of the article as shown in Figure 4 is symmetrical in that the layers at one side of the fabric substrate mirror those on the other. A asymmetrical structure also is possible wherein one or more layers at one side of the fabric do not appear at the other side. Accordingly, it should be appreciated that the article of the present invention also may include one or more layers of a non-metal or metal at one side or the other to provide dielectric properties or to provide other desirable properties including adherence to the fabric substrate or abrasion resistance. After application of the flame retardant directly to one or both sides of the fabric substrate, any number of layers can be built up by vapor deposition provided the materials are selected so that adjacent layers adhere one to another.

Samples of coated fabrics were formed and subjected to two tests. In a corrosion test, the fabric article is mated to a dissimilar metal and the surface resistance of the article is measured over time. The articles also are subjected

FOUO E F 2360

to a flammability test that generally follows the Underwriters Laboratories test procedure for a vertical burn of very thin materials (VTM). The UL vertical burn test is a standard test more fully described in UL publication titled "Test for Flammability of Plastic Materials for Parts in Devices and Appliances" which is incorporated herein by reference.

The UL publication may be consulted for details of the test procedure. However, for purposes of the present invention it is sufficient to say that in the Thin Material Vertical Burning Test, the test specimens are cut to a size of about 200 x 50 mm. The specimen is suspended so its longitudinal axis is vertical. A controlled flame is applied to the middle point of the bottom edge of the test specimen. After about three seconds, the flame is withdrawn (dropped vertically from its initial position) at a rate of about 300 mm/sec to a distance of about 150 mm away from the specimen. Simultaneously, a timing device commences the measurement of the Afterflame Time (t_1). "Afterflame Time" is defined as the time a material continues to flame, under specified conditions, after the ignition source has been removed.

When the specimen has stopped flaming, the burner is placed about 10mm from the specimen for another three seconds and again withdrawn and the Afterflame Time measured a second time (t_2) and the Afterglow Time (t_3) also is measured. "Afterglow Time" is defined as the time a material continues to glow under specified test conditions after the ignition source has been removed and/or the cessation of flaming. For a rating of zero, both t_1 and t_2 must be less than ten seconds and the sum of t_2 and t_3 must be less than thirty seconds.

For purposes of the Vertical Burn Test, control samples were made using a woven rip-stop 30 denier nylon fabric having a 130 X 130 warp and weft yarn count. All samples ranged between about 0.10 and 0.12 mm thick.

For Sample A, the fabric first was coated with silver using an electroless plating process. The silver saturated and permeated the fabric and formed a silver layer about 3000 Å thick on at least one side of the fabric. The

corresponding to Samples E-F are prepared by applying a flame-retardant coating about one mil thick directly to the surface of a polymeric rip-stock fabric. A metal coating then is applied by vapor deposition directly over the flame-retardant layer. As described above the metal is deposited in three layers comprising an adherence layer, a conductive metal and an abuse/corrosion resistant layer. These, in particular were 250Å Nichrome alloy, 3000Å silver and 250Å Nichrome alloy.

For corrosion testing, the articles were mated to surfaces of dissimilar metals including aluminum, zinc and chromate and the surface resistance of each sample was periodically measured to determine the conductivity of the sample. At the start of testing, the surface resistance of all samples varied from 0.02 to 0.05 ohm/sq or less. After a full thirty days of testing the surface resistance of all samples was again measured. All samples having an initial surface resistance of less than 0.05 ohms/sq had a surface resistance after thirty days of 0.04 ohms/sq or less. The one sample having an original surface resistance of 0.05 ohms/sq had a surface resistance of 0.08 ohms/sq after thirty days. These articles comprising a flame-retardant layer disposed between the fabric and the metal layer, having a UL VTM vertical burn rating of zero and maintaining a high surface conductivity over time are embodiments of the present invention.

Another typical metal layer configuration as an alternative to the configuration of Samples E-F can be a 100Å thick layer of Inconel® alloy, 2000Å of silver and a 100Å surface layer of Inconel® alloy. Samples of this type having an initial surface resistance of about 0.11 ohms/sq had a surface resistance of about 0.35 ohms/sq or less.

Thus it should be appreciated that the present invention accomplishes its intended objects in providing a flame-retardant corrosion resistant conductive fabric. Isolating the polymeric fabric from the conductive metal layer by disposing a flame-retardant layer between the two provides an improved burn resistance as compared to applying the flame-retardant over the

metal layer. Resistance to corrosion by galvanic action also is improved. Applying a one mil flame-retardant coating directly to the fabric (Samples E and F) is seen to provide better flame-retardant protection and corrosion resistance than application of a face coating of the same thickness over the metal layer (Sample B).

- 5 While a preferred embodiment has been described, it should be appreciated that modifications may be made without changing the spirit and scope of the invention. For example, the flame-retardant coating may be applied directly to both sides of the fabric to provide additional protection.
- 10 Two-sided flame-retardant coating also used in cases where it is desired to metalize both sides of the fabric. Both sides may be metalized for example where the fabric article is used as a dielectric to provide capacitance coupling.

Having described the invention in detail, what is claimed as new is: